

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

Publication number:

**0 206 286  
A1**

12

## EUROPEAN PATENT APPLICATION

21 Application number: 86108459.8

51 Int. Cl.<sup>4</sup>: C 09 D 11/10

22 Date of filing: 20.06.86

30 Priority: 25.06.85 US 748768

71 Applicant: HOWTEK, INC., 21 Park Avenue, Hudson New Hampshire 03051 (US)

43 Date of publication of application: 30.12.86  
Bulletin 86/52

72 Inventor: Nowak, Michael T., 38 Meadowbrook Lane, Gardner, MA 01440 (US)

24 Designated Contracting States: DE FR GB IT

74 Representative: Endlich, Fritz, Dipl.-Phys., Postfach 1326 Blumenstrasse 8, D-8034 Germering (DE)

54 Ink jet printer ink.

57 A hot-melt subtractive ink for an ink jet printer is formed from a thermosetting resin having a high hydroxyl number and a solid organic solvent having a melting point less than 150 °C, together with a dye. The ink has excellent jetting characteristics, forms a hard, stable, print raised above the surface of the substrate, provides high dot resolution, and remains colorfast both in the ink jet printer and on the paper even though exposed to continued high temperature. It is non-toxic and odorless, and eminently suitable for office document preparation, among other applications.

**EP 0 206 286 A1**

## Background of the Invention

### A. Field of the Invention

The invention relates to printing inks for ink jet printers, and comprises a solid, hot-melt ink that is particularly suitable for subtractive color ink jet document printing.

### B. Prior Art

Inks that are to be utilized in document printing by ink jet application are subject to demanding and frequently conflicting limitations.

The first is that imposed by the substrate itself, which is typically a fibrous material (e.g. paper) when viewed on a microscopic level. On such a substrate, ink that is applied to it must not soak in and spread or "bleed" excessively, lest the sharpness of the image be unacceptably reduced. As an example of the degree of sharpness required, current applications require a resolution on the order of 240x400 (i.e. 240 dots per inch in the horizontal direction, and 400 dots per inch in the vertical direction) for text printing. High quality graphics printing requires resolutions extending up 600 dots per inch. Further, the ink must be resistant to abrasion, as well as to inadvertent transfer to adjacent materials. Additionally, since the document may be carried through a variety of climates, the ink must remain stable at temperatures ranging from -20 C to +150 C. These restrictions are fairly severe when applied to black ink, but are even more severe when applied to colored inks, since even minor changes in color are frequently noticeable.

In the case of inks that are to be applied by ink jet techniques, the problem is even further compounded by the requirement that the inks be compatible with jetting

requirements of the printer. Typically, this application imposes restrictions on, for example, the viscosity of the inks, so that the inks can be expelled from the jet as relatively uniform droplets without excessive

5 satelliting. Additionally, the constituents must all be compatible with each other, both physically (i.e. capable of forming a solution which can be jetted successfully) and chemically (i.e. not adversely affecting the stability or other characteristics of the materials).

10 Most of the inks heretofore utilized in ink jet printers have been aqueous solutions of water-soluble dyes. Examples of such inks are described in U. S. Pat. No. 3,846,141, issued Nov. 5, 1974 to D. G. Ostergren et al, and U. S. Pat. No. 4,512,807 to A. Ogawa et al. Inks  
15 of this type have been found acceptable for many applications, but do not have the desired hardness of the resultant print, not the requisite stability and sharpness for fine color applications.

An example of a non-aqueous ink jet ink is described  
20 in U. S. Pat. No. 4,390,369, issued June 28, 1963 to A. R. Merritt et al. The ink described therein utilizes a natural wax which is liquified by heating in order to jet it and which is thereafter solidified on contact with the substate, e.g. paper. Among other drawbacks, however, the  
25 resultant material readily abrades, and is thus unacceptable for most document purposes where some degree of print stability is required.

### Brief Summary of the Invention

#### 30 A. Objects of the Invention

Accordingly, it is an object of the invention to provide an improved ink for ink jet printers.

Further, it is an object of the invention to provide an ink for ink jet printers that is resistant to abrasion

and that is relatively stable over a wide range of temperatures.

Yet another object of the invention is to provide an ink for ink jet printers that possesses good jetting characteristics.

Still a further object of the invention is to provide an ink for ink jet printers that can form a sharp image of high resolution.

10        B. Brief Summary of the Invention

In accordance with the present invention, an ink jet printer ink is formed from a mixture of a thermosetting resin having a high hydroxyl number and a low acid number and comprising from about 5 to 40 w% (weight percent) of the resultant mixture, and a solid organic solvent characterized by a low acid number and comprising from about 60 to 95 w% of the mixture, together with a minor amount (on the order of about 1w% or less) of a temperature-stable subtractive dye. By "high hydroxyl number" is meant a hydroxyl number in excess of 50; by "low acid number" is meant an acid number less than 10.

In particular, in accordance with the preferred embodiment of the invention, the resin comprises a polyester, specifically, a linear saturated polyester resin of low molecular weight (i.e. in the range of from 50 to 10,000) and low acid number but high hydroxyl number. From observation of this and other materials tested, it is believed that the presence of significant hydroxyl content provides substantial hydrogen bonding which maintains the integrity of individual drops as they are expelled from the jet, despite the substantial temperature (on the order of 125 C) and pressure to which they are subjected during expulsion. This results in ink droplets which are uniform and fine, and which are

relatively free of satellites as they travel to the paper.

An excellent example of such a resin, and one that has been found especially satisfactory herein, is sold under the trade name Desmophen 650A-65 by Mobay Chemical Corporation and has a hydroxyl number in the range of from 155-190. Its characteristics are described more fully hereinafter. The preferred solvent comprises toluenesulfonamide, particularly a mixture of ortho- and para-toluenesulfonamide. Such a mixture lowers the resultant melting point and thus allows jetting at lower temperatures. A particularly suitable solvent has been found to be the solvent sold under the trademark "Santicizer 9" by the Monsanto Chemical Corp., as also described more fully hereinafter.

#### Detailed Description of the Invention

A mixture was formed by adding 10 parts by weight of Desmophen 650A to 90 parts by weight of Santicizer 9 to form a base for a dye. A stabilizer in the form of a phosphite antioxidant (approximately 1wt%) was then added. A magenta subtractive ink was then formed by adding to the mixture .75 parts by weight of Atlantic Atlasol Magenta M (Solvent Red 49). Similarly, yellow, blue and black inks for subtractive printing were obtained by adding to the base mixture .6 parts by weight of Atlantic Atlasol Yellow BB (Solvent Yellow 42), 0.4 parts by weight of Ciba Geigy Orasol Blue GN (Solvent Blue 67), and 2.0 parts by weight of Sandoz Sayinyc Black RLS (Solvent Black 45).

The resin and solvent used in the foregoing example have the following principal characteristics:

	Desmophen 650A	Santicizer 9
hydroxyl number	155-190	

acid number	3.0 (max)	pH 4.0
(min)		
specific gravity	1.17	1.353
crystallizing point		105 C
5 boiling point		214 C
flash point	49 C	
molecular weeight	325 (average)	171

The materials are non-toxic, and have essentially no odor.

10       The resultant mixtures were jetted onto a paper  
substrate through a plastic jet having a diameter of on  
the order of .03 inches at frequencies up to in excess of  
10,000 Herz and at a temperature of on the oder of 125 C.  
The print copy so formed was characterized by a raised  
15 texture similar to engraving, and of excellent dot  
resolution and sharpness. The print was hard and  
resistant to abrasion, as well as to transfer from  
document to document. It dried quickly on the surface of  
the paper, but nonetheless formed a tenacious bond with  
20 it. The color remained stable, without appreciable color  
shift, even when subjected to a temperatures on the order  
of 150 C for a week. The ink did not clog the jet even  
when left in it for extended periods of time at the  
jetting temperature, and it remained stable in the jet  
25 printer at a temperature of 150 C for weeks. The ink  
possessed a viscosity well within the desired range of  
from 5 to 30 centipoise and , specifically, its viscosity  
was approximately 17 centipoise; it jetted consistently  
without significant satelliting.

30       The ink described herein has been found particularly  
useful in connection with an ink jet printer using a  
plastic jet that is the subject of a related application.  
The jet described therein is formed is formed from a  
polyetheretherketone material. As described in that  
35 application, such a material has many characteristics  
that render it advantageous for use in forming an ink jet

but it is nonetheless susceptible to attack by many of the inks commonly used for such purposes. The present ink does not attack that material, and is thus highly desirable for use with it, although its application is  
5 not so limited.

#### CONCLUSION

From the foregoing it will be seen that I have provided an improved ink for ink jet printers. The ink  
10 has excellent jetting characteristics, forms a hard, stable, print raised above the surface of the substrate, provides high dot resolution, and remains colorfast both in the ink jet printer and on the paper even though exposed to continued high temperature. It is non-toxic  
15 and odorless, and eminently suitable for office document preparation, among other applications.



D75-010

1           1. A hot-melt ink for ink jetprinters, consisting  
2           primarily of a thermosetting resin having a high hydroxyl  
3           number and a solid organic solvent having a melting point  
4           less than 150 C, together with a minor portion of dye  
5           material.  
6

1           2. A hot-melt ink according to claim 1 in which said  
2           hydroxyl number is in excess of 50.  
3

1           3. A hot-melt ink according to claim 2 in which said  
2           resin consists of a linear saturated polyesterresin of  
3           low molecular weight.  
4

1           4. A hot-melt ink according to claim 1 in which said  
2           solvent consists primarily of an aromatic sulfonamide.  
3

1           5. A hot-melt ink according to claim 4 in which said  
2           solvent consists primarily of toluenesulfonamide.

1  
2           6. A hot-melt ink according to claim 1 in which said  
3           solvent consists primarily of a primary sulfonamide.

1        7. A hot-melt ink according to claim 1 in which said  
2 solvent consists primarily of a mixture of ortho- and  
3 para-toluenesulfonamide.

4

5

6

7        8. A hot-melt ink comprising from 5 to 40 parts by  
8 weight of a linear saturated polyester resin of high  
9 hydroxyl number and low acid number and from 95 to 60  
10 parts by weight of a solid organic solvent having a  
11 melting point less than 150 C, together with a color-  
12 subtractive dye.

13

1        9. A hot-melt ink according to claim 8 in which said  
2 solvent comprises an aromatic sulfonamide.

3

1        10. A hot-melt ink according to claim 9 in which said  
2 solvent comprises toluenesulfonamide.



European Patent  
Office

# EUROPEAN SEARCH REPORT

0 206 286

EP 86 10 8459

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
A, D	US-A-4 390 369 (A.R. MERRITT)  * Abstract *		C 09 D 11/10
A	--- US-A-4 218 362 (SATORU HONJO)  * Claims 1, 4 *  -----		
			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
			C 09 D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 01-10-1986	Examiner GIRARD Y.A.
<b>CATEGORY OF CITED DOCUMENTS</b>			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons  & : member of the same patent family, corresponding document	